

## PUREFILL 2

Composite nano-hybride antéro-postérieur


Sans HEMA, TEGDMA, Bis GMA

### Points forts

Taux de conversion : > 70%.

Ne colle pas aux instruments.

Faible taux de rétraction : ~ 2.2 %.



Formule plus malléable  
pour une utilisation plus aisée.

Stable, ne polymérise pas sous le scialytique.

Profondeur de polymérisation > 3mm.

### Indications

- Restaurations postérieures (classe I, classe II, MOD).
- Restaurations antérieures (classe III et classe IV).
- Cavités de classe V.
- Corrections esthétiques (diastèmes, hypoplasies, décolorations).



Ce composite, 100% fabriqué en France, est le premier composite Elsodent dont la formule innovante ne contient aucun monomère dégradable comme le TEGDMA, Bis GMA ou l'HEMA. Sa biocompatibilité, associée à une très basse toxicité dans le temps, en font un produit incontournable dans une démarche assumée de santé publique.

### Références & Présentations

**PUR2-3-\*** Seringue de 3g. Teintes VITA : A1/B1 - A2 - A3 - A3,5 - B2.


**PUR2-5\*** Boîte de 20 compules de 0.25g, dans les teintes VITA A1/B1 - A2 - A3 - A3,5 - B2.

\* Précisez la teinte.


Dispositif médical de classe IIa certifié par TÜV Rheinland (0197).

## TESTS PHYSICO-CHIMIQUES COMPARATIFS


Taux de rétraction\*



Résistance à la flexion\*



Taux de conversion\*




\* Tests réalisés par G-Pharma suivant les normes : Taux de rétraction : norme ISO 17304 ; Résistance à la flexion : Tests effectués selon la norme ISO4049 : à l'aide d'un banc de test Zwick. Taux de conversion : Tests effectués par infrarouge en mode ATR. La polymérisation a été faite à l'aide d'une lampe Elsdodent de 9mm de diamètre et d'une puissance de 600mW/cm<sup>2</sup> à température ambiante (20°C).

## PUREFILL 2

**Nano-hybrid, antero-posterior composite**  
**HEMA, TEGDMA, Bis GMA and BPA-free\***

### Features



### Indications

- Posterior restorations (class I, class II, MOD).
- Anterior restorations (class III and class IV).
- Class V cavities.
- Aesthetic corrections (diastema, hypoplasia, discoloration).



This is the first Elsodent composite developed from an innovative Bis GMA, TEGDMA, HEMA-free formulation, to get a low toxicity composite. Its higher biocompatibility, due to the non-hydrolysable monomers contained in the matrix of the product, leads to a lower toxicity over time. It makes PureFill an essential product in our declared approach to public health. The results of comparison tests show the astonishing qualities of PureFill.

### References & Presentations

**PUR2-3\*** 3g syringe. Available in the following VITA shades: A1/B1 - A2 - A3 - A3,5 - B2.

**PUR2-5\*** 20 x 0,25g compules. Available in the following VITA shades: A1/B1 - A2 - A3 - A3,5 - B2.

\* Shade


MD : Class IIa certified by TÜV Rheinland (0197).

## Important Notice


There is a clear correlation between the conversion rate (polymerization rate) of composites, their toxicity and their shrinkage during polymerization: the higher the conversion rate, the higher the shrinkage and the lower the cytotoxicity will be. Furthermore, we note that with a conversion rate above 70%, (the highest of all the products tested), the shrinkage of PureFill 2 is still one of the lowest of all the composites sold on the market.

## PHYSICO-CHEMICAL COMPARATIVE TESTS


Shrinkage\*



Flexural Strength\*



Conversion rate\*



\* Tests conducted by G-Pharma. Volumetric shrinkage was determined by dentistry measurements according to Archimedes Principe and ISO 17304-2013. Flexural strength: tests carried out with a Zwick equipment following the ISO 4049 : 2009 norm. Conversion rate : the degree of conversion was evaluated using a FTIR spectrometer with an attenuated total reflectance (ATR) accessory. The polymerization has been conducted by an Elsodent lamp: 9mm of diameter and 600mW/cm<sup>2</sup> power at room temperature (20°C).